Chemical Name	Footnote	Nitrile	Nitrile PVC	CPE	Hypalon™	Polyester	Teflon"				
Acetic Acid (25%)	2	Х	2	1	2	Х	1				
Acetone	X	Х	X	1	Х	Х	1				
Acetylene	NO HOSE AVAILABLE										
Air (71°C, 166°F)	1	1	1	1	1	1	1				
Air (82°C, 180°F)	2	2	2	1	2	2	1				
Air (93°C, 199°F)	X	X	X	1	2	X	1				
Amyl Acetate	X	Х	Χ	2	X	Х	1				
Aniline	X	Х	X	2	Х	_	1				
Benzene (Benzol)	X	Х	X	Х	X	Х	1				
Butyl Acetate	X	Χ	X	2	X	X	1				
Butyl Alcohol (Butanol)	2	X	X	1	2	2	1				
Carbon Dioxide (Dry)	2	1	1	1	1	_	1				
Carbon Dioxide (Wet)	2	1	1	1	1	_	1				
Carbon Disulfide	X	X	X	2	X	_	1				
Chlorine Gas (Dry & Wet)		,,,	NO HOSE A								
Chlorine Water (25%)	X	Χ	X	_	2	X	1				
Chloroform	X	X	X	_	X	X	1				
Cyclohexane	X	2	X	1	X	2	1				
Diesel fuel (under 50°C, 122°F)	X	1	X	2	X	1	1				
Ethers (under 50°C, 122°F)	X	2	2	1	2	X	1				
Ethyl Acetate	X	X	X	2	X	2	1				
Ethyl Alcohol (Ethanol)	1	1	_	1	1	2	1				
Ethyl Cellulose	_	_	_	1	_	_	1				
Ethyl Chloride (Wet)	2	X	Х	_	X	_	1				
Ethylene Glycol (under 66°C, 151°F)	1	1	1	1	1	1	1				
Fluorine (Liquid)	ı	'	NO HOSE A			'	•				
Formaldehyde 37%	2	2	-	1	2	2	1				
Fuel A (ASTM)	X	2	2	1	1	_	-				
Fuel B (ASTM)	X	2	X	2	X	_	_				
Fuel Oil	X	1	X	1	X	2	1				
Glycerine (Glycerol)	1	1	1	1	1	1	1				
Grease (Petroleum Base)	2	1	2	_	2	1	1				
,		1		2	1		1				
Hexane (under 50°C, 122°F)	X		2		1	2					
Hydraulic Fluid (Phosphate Ester Base)	X	X	X	1		2	1				
Hydrochloric Acid (37%) Hydrogen (Gas)	X 1	1	X –	1	2	X 2	1				
Hydrogen Peroxide (30%)	X	2	X	1	2	X	1				
Isopropyl Alcohol	2	2	2	1	2	-	1				
Kerosene	X X	2	X	1	X	2	1				
L.P.G.	USE L.P.G. HOSE ONLY		0	4	0	4	4				
Lubricating Oils (under 50°C, 122°F)	2	1	2	1	2	1	1				
Methyl Oblasida	1	1	1	1	1	2	1				
Methyl Chloride	X	X	X	X	X	2	1				
Methyl Ethyl Ketone (MEK)	X	X	X	2	X	2	1				
Naphtha (Low Aromatics)	X	2	X	1	X	X	1				
Natural Gas	USE L.P.G. HOSE ONLY										
Nitric Acid (10%)	X	X	X	1	2	X	1				
Nitric Acid (40%)	X	X	Х	X	X	X	1				
Oxalic Acid (10% cold)	X	Χ	Х	1	2	X	1				
Ozone (Dry)	2	X	2	1	2	2	1				

Paint Solvents (Oil Base)	Χ	X	_	_	Χ	2	1			
Perchloroethylene	Χ	X	Χ	2	Χ	X	1			
Phenol (Carbolic Acid)	Χ	X	Χ	1	Χ	Χ	1			
Phosphoric Acid (50%)	2	2	Χ	1	1	Χ	1			
Propane Gas	USE L.P.G. HOSE ONLY									
Sodium Hydroxide (40%)	1	2	_	1	1	Χ	1			
Sodium Hydroxide (50%, under 45°C, 113°F)	2	X	Χ	1	1	Χ	1			
Sulphuric Acid (10%)	1	X	2	1	1	Χ	1			
Sulphuric Acid (93%)	Χ	X	Χ	_	Χ	Χ	1			
Toluene (Toluol)	Χ	X	Χ	Χ	Χ	2	1			
Trichloroethylene	Χ	1	Χ	2	Χ	2	1			
Vegetable Oils	2	X	2	1	2	1	1			
Xylene	Χ	X	_	Χ	_	2	1			